

Product Details

Product Name : HIPOL B60 MB
Product CAS no. : 68648-78-2

HIPOL B60 MB is a novel low viscosity grade of Polyvinylbutyral resin offered by MICRO INKS LIMITED. HIPOL B60 MB is latest addition to the standards of HIPOL resins offered for printing Inks, Paints, Coatings, Adhesives and Ceramics.

Specifications

| | |
|--|---------------------|
| Physical Appearance | White fluffy powder |
| Viscosity in sec @30 ⁰ C (10% Ethanol in B4 Ford cup) | 55-60 |
| Volatile Content (%w/w max) | 2 |
| Acid Value(mg KOH/gm) | 1 max |

General Properties

HIPOL B60 MB offers following unique properties

1. Excellent adhesion to metals, plastics, glass, ceramics, wood, concentrate, leather etc.
2. With very large surface area combined with low molecular weight, product undergoes into solution under mild agitation in a very short time to offer clear transparent solution with minimum loss of solvent.
3. Product is soluble in low cost environment friendly solvents like alcohols, glycol ethers & has ability to accept ester, ketones etc.
4. Excellent film formation property. Film being clear, transparent, odourfree & tasteless.
5. Excellent pigment wetting in non-aqueous medium.
6. Excellent compatibility with other film forming resins like N.C., Epoxy alkyds, phenolics, cellulosics etc.
7. Free hydroxyl groups present in HIPOL are chemically reactive & undergo reactions with phenolics, epoxies, isocyanates, melamine aldehyde resins etc.
8. Being lowest molecular weight resin of HIPOL series offers excellent flexibility. Product also shows good adhesion resistance, heat resistance, resistance to water and wide range of other chemicals.
9. HIPOL B60 MB is a thermoplastic resin with low softening temperature & hence shows good heat sealing properties. Thermoplasticity can be reduced or eliminated completely by cross linking reaction involving free hydroxy groups.

Applications

HIPOLB60 MB is an ideal choice where high solid & with low viscosity is the basic requirement.

HIPOL B60 MB finds applications in following areas:

HIPOL B60 MB with its unique combination of physical and chemical characteristics is an ideal binder for flexographic/ gravure printing inks for surface printing as well as lamination applications in flexible packaging involving substrates like polyester, BOPP, Polyethylene, PVDC coated pp, acrylic coated PP, cellulose acetate, cellophane, polystyrene, polyamide films. Also HIPOL B60 MB is an ideal binder for production of pigment chips, thermal transfer printing inks, varnishes etc.

Printing Inks

HIPOL B60 MB offers good water resistance coupled with good blocking resistance, good flow and excellent pigment wetting properties, hence is ideal for formulation of gravure and flexographic printing inks.

Stability : Stable

Hazardous Polymerization : Will not occur

Conditions to avoid : Heat, Open Flame or other sources of ignition.

Heat-sealing Lacquers

HIPOLB60 MB with low softening temp offers lower sealing temperature. However further reduction in sealing temperature could be achieved by incorporation of plasticizer and heat sealing temperate could be increased by incorporating nitrocellulose.

Two-pack Paints

Low molecular wt., high functionality because of free hydroxyl groups helps use of HIPOL B60 MB formulation on non yellowing stoving finishes for metals and metal foils. Crosslinking could be achieved with resins like phenolic resins, melamine, urea etc. Coating formulations curing at room temperature are obtained by combining HIPOL B60 MB with urea resins using mild solvents. Cured coatings show water and alcohol resistance and bear high mechanical stresses and find application as floor sealers for indoor and outdoor application.

Shelf Life

Recommended for use within one year of date of manufacture.